TABLE 1

Test piece	Temperature	Stress	Life	Elongation	Reduction	LMP
(No.)	(°C)	(kgf/mm2)	(h)	(%)	(%)	P=20
						(×1000)
1	900	40	310.6	13.4	14.3	26.387
2	1100	14	85.3	16.7	37.8	30.114
3	900	40	402.2	10.1	15.1	26.519
4	1000	25	152.5	14.9	15.9	28.243
5	1100	14	126.3	14.9	26.3	30.349